



WesternLime

---

## WESTERN DOLOMITIC PEBBLE LIME

### Typical Analysis

Calcium Oxide	CaO	57.67%
Magnesium Oxide	MgO	40.45%

### Additional Tests

Loss on Ignition	<1.00%
Reactivity ASTM	+35° rise in 3 min.

### Material Sizing

3/4 " x 1/4"

or

2" x 1/4" metallurgical grade

\*All information is based on averages. Normal variations can be expected in daily shipments.