



WesternLime

HIGH CALCIUM PEBBLE LIME

Typical Analysis

Available Calcium Oxide	CaO	92.00% ± 0.5%
Magnesium Oxide	MgO	2.0% ± 0.5%

Additional Tests

Loss on Ignition	<1.5%
Residue after Slaking	1.50% avg.
Reactivity AWWA	40° rise in 3 min.
Bulk Density	50 lbs./cu.ft.

Material Sizing / Applications / Availability

US	Metric	Common Application:	Available at:	
1 1/2" x 3/4"	38 mm x 19 mm	Metallurgical	Port Inland, MI	
3/4" x 1/4"	19mm x 6.4 mm	Metallurgical, Water, FGD, Paper, Metallic Mining	Green Bay, WI	Port Inland, MI
1/4" x 0"	6.4 mm x 0 mm	FGD, Soil Stabilization	Green Bay, WI	Port Inland, MI

Western Lime Corporation's High Calcium Lime complies with ASTM C-911, meets ANSI/AWWA B202 Standards, and meets ANSI/NSF 60 Standards for Drinking Water Additives.

All information is based on averages. Normal variations can be expected in daily shipments