



WesternLime

206 North Sixth Avenue  
West Bend, WI 53095-0057  
Office: 262-334-3005  
Fax: 262-334-2874

## WESTERN MASON'S BLEND TYPE N

Western Type S Hydrated Lime & Type I Portland Cement Blend

WATER RETENTION 95.4

Initial Flow 111  
Final Flow 106

AIR CONTENT 8.0

### COMPRESSIVE STRENGTH (PSI)

7 day 1243  
7 day 1256  
7 day 1249  
  
28 day 1846  
28 day 1925  
28 day 1810

### FLEXURAL BOND STRENGTH (PSI)

Standard Deviation 21.55  
COV 12.62  
Corrected PSI 134.26

Meets and exceeds the Property Specification for ASTM C-270  
"Standard Specification for Mortar for Unit Masonry"