



WesternLime

206 North Sixth Avenue
West Bend, WI 53095-0057
Office: 262-334-3005
Fax: 262-334-2874

WESTERN MASON'S BLEND TYPE S

Western Type S Hydrated Lime & Type I Portland Cement Blend

WATER RETENTION 94.7

Initial Flow 114
Final Flow 108

AIR CONTENT 8.3

COMPRESSIVE STRENGTH (PSI)

7 day 2062
7 day 2154
7 day 2090

28 day 2794
28 day 2716
28 day 2835

FLEXURAL BOND STRENGTH (PSI)

Standard Deviation 15.67
COV 9.58
Corrected PSI 137.18

Meets and exceeds the Property Specification for ASTM C-270
"Standard Specification for Mortar for Unit Masonry"