



WesternLime

206 North Sixth Avenue
West Bend, WI 53095-0057
Office: 262-334-3005
Fax: 262-334-2874

WESTERN MASON'S BLEND TYPE M

Western Type S Hydrated Lime & Type I Portland Cement Blend

WATER RETENTION 95.4

Initial Flow 110
Final Flow 105

AIR CONTENT 7.6

COMPRESSIVE STRENGTH (PSI)

7 day 2793
7 day 2710
7 day 2832

28 day 3346
28 day 3456
28 day 3493

FLEXURAL BOND STRENGTH (PSI)

Standard Deviation 21.22
COV 12.46
Corrected PSI 143.68

Meets and exceeds the Property Specification for ASTM C-270
"Standard Specification for Mortar for Unit Masonry"