



WesternLime

206 North Sixth Avenue  
West Bend, WI 53095-0057  
Office: 262-334-3005  
Fax: 262-334-2874

## WESTERN COLORED MASON'S BLEND TYPE S

Western Type S Hydrated Lime & Type I Portland Cement Blend

WATER RETENTION 94.7

Initial Flow 114  
Final Flow 108

AIR CONTENT 8.3

### COMPRESSIVE STRENGTH (PSI)

7 day 2062  
7 day 2154  
7 day 2090

28 day 2794  
28 day 2716  
28 day 2835

### FLEXURAL BOND STRENGTH (PSI)

Standard Deviation 15.67  
COV 9.58  
Corrected PSI 137.18

Meets and exceeds the Property Specification for ASTM C-270  
"Standard Specification for Mortar for Unit Masonry"